



272A South Industrial Drive  
Prince Albert, SK.  
S6V 7L8  
Phone: 306-922-4814  
Fax: 306-922-4817  
Email: [apasloski@pazperformance.com](mailto:apasloski@pazperformance.com)  
Web [www.pazperformance.com](http://www.pazperformance.com)

## DATASHEET

<b>Article:</b>	<b>25560</b>
Composition :	56%/ 39%/ 5 % Polyethylen/ Polyester Hydropur®/ Elasthan
Colour:	white
Construction:	Interlock, Doubleface  Polyethylen = outer side Polyester = inner side
Weight:	400 g/m <sup>2</sup> +/- 5%
Cut resistance, EN 388:2004 § 6.2:	cut level 3 (IFTH Test report N° 11-00070)
Shrinkage after 5 washing cycles <u>60°C</u> :	+/- 3% DIN EN 25077/ ISO 6330: 2001:process 2A/E50
Hydrophilic property:	wetting index: $i_B$ : < 1,0 s
Antibacterial property:	=/> 99% according Shake Flask Test ASTM E 2149-01
Certificates FTT:	ISO 9001 and Ökotex Standard 100 (product class II – direct skin contact)

November 19, 2013

This information corresponds to our current knowledge on this subject. It is offered solely to provide possible suggestions for our own consideration. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variation in end use conditions, Paz Performance makes no warranties and assumes no liability in connection with any use of this information.